

Product designation: COLORBRITE AC
Product code: JW10-9C9X
Colour: VWL C9X deepblack

Properties

Effect waterborne basecoat

Resin base

Binder dispersion

Physical values

Delivery viscosity (DIN 53019; 1000s-1, 23°C)	[mPas]	:	60 - 80
Spray viscosity (DIN 53019; 1000s-1, 23°C)	[mPas]	:	60 - 80
Solid content, delivery (DIN EN ISO 3251; 1h 125°C)	[weight%]	:	18 - 22
Density, delivery (23°C) (DIN 53217)	[g/cm ³]	:	1,00 - 1,04
pH-Value (DIN ISO 976)		:	7,8 - 8,2
Storage stability		:	6 months at temperature >5°C till <35°C
Process layer	[µm]	:	10 - 15
Flash off time		:	5 - 10 min. at 23°C
Intermediate drying process		:	10 - 15 min. at 60 - 80 °C
Relative humidity	[%]	:	65 +/-5
Cabin temperature	[°C]	:	23 +/-2

Primer

Primerless

Application

1st layer pneumatic or ESTA / 2nd layer pneumatic

Safety datas

Flashpoint (DIN 53213) [°C] : > 61

Characteristics according Safety-Data-Sheet

Basecoat is thixotropic; please stir well done and carefully before usage

Version: 19.11.2010

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply and guarantee of neither certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are the general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH
Paradiesstrasse 18-22
97080 Würzburg
Tel.: +49 931 9084-0
Fax: +49 931 9084-264